

Application No. 10/564,674
Response dated June 8, 2009
In Reply to Office Action of December 8, 2008
Attorney Docket No. 0470-060131

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Application No. : 10/564,674
Applicants : MARCEL WIJLAARS et al.
Filed : July 14, 2006
Title : TISSUE SUBSTITUTE MATERIAL
Art Unit : 1615
Confirmation No. : 1707
Examiner : Caralynne Helm
Customer No. : 28289

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

DECLARATION UNDER 37 C.F.R. §1.132

I, Jacques Marie René Jan Huyghe declare as follows:

1. I am a citizen of the Netherlands and reside at Sijsjesstraat 3, 2340 Beerse. I graduated from Ghent University (Belgium) in 1979 and received a Master's degree in Civil Engineering. I obtained a Ph.D. degree from Eindhoven University of Technology (The Netherlands) in 1986. I have had 30 years of experience within the field of Biomechanics and Mechanics of Materials, working for the Belgian Ministry of Defense, University of Twente (The Netherlands), Eindhoven University of Technology (The Netherlands) and Maastricht University (The Netherlands). Additionally, I am the author of the publications related to the field of biomechanics, engineering mechanics and prosthesis design and indexed in Exhibit A which is attached hereto. I am also one of the inventors of the subject-matter for which US 10/564,674 is filed.

2. I have read and am thoroughly familiar with the contents of the above-identified patent application. Furthermore, I have read and understand the Office Actions issued by the United States Patent and Trademark Office on March 28, 2008 and December 8, 2008 and the issues and prior art references listed therein, specifically Malmonge et al. (Artificial Organs 2000, 24:174-178) (hereinafter "Malmonge"), Pissis et al. (Proceedings of the 10th International Symposium on Electrets 1999 p. 561-564) (hereinafter "Pissis"), Young et al. (Biomaterials 1998: 1745-1752) (hereinafter "Young") and Kou et al. (Journal of Controlled Release 1990 12:241-250) (hereinafter "Kou").

3.

The invention concerns a material for cartilage-like material substitution, comprising a fiber-reinforced polymerized hydrogel, wherein said polymerized hydrogel contains 10-70% (m/m) swellable fibers (based on the dry matter), wherein the length of the fibers is at least a millimeter, and wherein 1-5% (m/m) (based on the dry matter) of a substance that contains ionized groups has been added-to said polymerized hydrogel.

4.

As an expert in the field of Biomechanics and Mechanics of Materials, it is my opinion based on the disclosure of Malmonge in view of Pissis and Young, that claim 8-9 and 12-14 would



not have been obvious at the time the invention was made to a person having ordinary skill in the art to which said subject matter of claims 8-9 and 12-14 pertains.

In my opinion, any combination of the teachings of Malmonge, Pissis and Young would not result in a material suitable for cartilage-like material substitution, comprising a fiber-reinforced polymerized hydrogel, wherein said polymerized hydrogel contains 10-70% (m/m) swellable fibers (based on the dry matter), wherein the length of the fibers is at least a millimeter, and wherein 1-5% (m/m) (based on the dry matter) of a substance that contains ionized groups has been added-to said polymerized hydrogel, for the reasons set forth below.

5.


Malmonge describes a copolymer of 2-hydroxyethyl methacrylate (HEMA) and acrylic acid (AA) as artificial articular cartilage material. Acrylic acid ionizes into acrylate and Na^+ , which is believed to result in swelling of the HEMA-AA copolymer and to contribute to the compressive strength of the cartilage material (page 175, column 1, paragraph 1). Malmonge is solely concerned with mechano-electrical transduction of the HEMA-AA copolymer and its dependence on acrylic acid content of the copolymer. Malmonge nowhere addresses the problem of providing adequate strength and tougher mechanical properties to the hydrogel.

6.

Pissis is directed towards the dielectric and water sorption properties (see title and Introduction, final sentence) of a poly(hydroxyethyl acrylate) (pHEA) gel reinforced with Nylon nanoparticles, prepared by a tedious procedure of cutting, boiling in strong acid and ultra-sonification of what once used to be fibers (Experimental, lines 8-14).

Pissis is not at all concerned with further improving the toughness of the gels; hence, there are no pointers in Pissis for applying millimeter or greater sized fibers.

Furthermore, in the nanoparticle-reinforced hydrogel according to Pissis swelling due to water sorption is confined to the PHEA hydrogel phase, and does not affect the nylon nanoparticles (see page 563, final 3 sentences); this stands in contrast to the claimed invention, wherein the fibers by itself are swellable (claim 8) and wherein a considerable volume increase can be achieved by penetration of aqueous monomer solution into the fiber prior to polymerization (see page 2, paragraph 2 and Exhibit C).



7. (added paragraph w.r.t. template Webb)

Young describes an artificial skin substitute material for wound dressing usage (Introduction, final sentence) consisting of a 2-hydroxyethyl methacrylate (HEMA) polymer hydrogel reinforced with woven or knitted nylon and elastic spandex fibers, gauzes and low lint wipers. The flat and smooth artificial skin substitute materials according to Young are characterized by being ultrathin (0.23 mm or thinner) and containing very small amounts (< 1.66 wt%) of fiber. Inherent to its intended use as wound dressing, there is no mention of the compressive properties of the reinforced hydrogel membrane according to Young.

8.

The success of the claimed invention is demonstrated in Exhibit B, where a fiber-reinforced hydrogel network is compared to a reference hydrogel network. Both samples are equilibrated with a physiological salt concentration, i.e. concentration of sodium chloride of the external bath in which the samples are equilibrated at 0.15 moles/l. After equilibration, the samples have sizes in the order of 1 cm and are tested under compression in a high humidity environment. It is shown in the attached exhibit B that the use of swellable fibers in a gel sample improves the toughness of the gel under compression. Brittle fracture can be avoided using the swellable fibers in the gel. Only minor damage is observed on the surface of the fiber-reinforced hydrogel (picture in the lower left of Exhibit B). The integrity of the sample is not affected by this minor damage. The brittle fracture seen for the non-reinforced hydrogel destroys the integrity and load-bearing capacity of the gel (picture in lower right of Exhibit B).

9.

Malmonge nowhere addresses the problem of providing adequate strength and tougher mechanical properties to the hydrogel and, as such, does not teach or suggest to include any additional material, let alone millimeter or greater sized fibers, in the polymer gel.




Although Pissis does describe the reinforcement of a polymer gel network, its solution is to provide the network with a dispersion of nanometer-sized Nylon particles. Pissis is not at all concerned with further improving the toughness of the gels; hence, there are no pointers in Pissis for applying millimeter or greater sized fibers. Therefore, the combination of Malmonge and Pissis does not yield the claimed fiber-reinforced polymerized hydrogel for artificial cartilage. Even if erroneously interpreting the term "particles" in Pissis to mean "fibers", the dimensions of the particles in Pissis [page 1 line 10 from the bottom ("... a fine suspension of Nylon nanoparticles in water ...")] differ from the claimed fibers by a factor 1,000,000.

Moreover, Pissis teaches away from adjusting the length scales of the Nylon nanoparticles or to increase their concentration to above 10 wt% in order to prevent any agglomeration (page 561, final sentence: *"The maximum weight percentage of nanoparticles in the hydrogel that could be thus obtained was 10%; above this value the nanoparticles tend to agglomerate and their water suspension resulted in a gel-like paste which makes it unsuitable for mixing with the monomer mixture"*).

Young is concerned with an artificial skin substitute material for advanced wound dressing usage. Accordingly, Young solely discloses smooth, essentially two-dimensional ultrathin woven or knitted (see Abstract) hydrogels, for which elastic strain rather than compressive strength is a prerequisite. Since the invention is concerned with artificial cartilage material, which is generally characterized by a thickness of at least 1, preferably at least 2 mm, there are no pointers for consulting Young, let alone combining the teachings of Young with the prior art.

Nonetheless, even if the skilled person would consider Pissis and/or Young, he would not arrive at the claimed invention. Instead, he would at most come up with a composite comprising very small amounts (<10 wt%, Pissis; <1.66 wt%, Young) of nanometer-sized particles (Pissis) or flat, ultrathin (< 0.23 mm) woven or knitted nylon or spandex fibers (Young). Such a composite would much more resemble the non-fiber-reinforced reference sample of Exhibit B and its compressive strength. In this respect, any reasoning leading to other forms of fiber reinforcement, such as those with large (> 10 wt%) amounts of millimeter-sized fibers, would reflect impermissible hindsight bias.



10. Additionally, as an expert in the field of Biomechanics and Mechanics of Materials, it is my opinion based on the disclosure of Malmonge in view of Pissis and Kou, that claims 8 and 10 would not have been obvious at the time the invention was made to a person having ordinary skill in the art to which the subject matter of claims 8 and 10 pertains.

11.

Kou is concerned with the mechanism of drug release from methacrylate-methacrylic acid polymer hydrogels. No mention of possible applications as cartilage substitute material is made. Kou nowhere addresses the problem of improving the toughness of such gels, let alone that it suggests reinforcement with long fibers for solving this problem.


12.

Exhibit C shows the swelling of a fiber in a monomer solution of pHEMA as visualized under a light microscope. A Lycra™ fiber (Dupont de Nemours) 17 dtex is submersed in a monomer solution of HEMA and 2 % of methacrylate, prior to the addition of initiator. This fiber has the ability of a surprisingly high-strength bonding with the pHEMA-gel with added methacrylate. The fiber is observed using light microscopy. In a short time the Lycra™ fiber increases its diameter by factor of more than 3. The length of the fiber is increased as well (not shown on the picture), although not in the same proportion as the diameter. The increase in diameter indicates a dramatic increase in volume, which can only be explained by imbibition of monomer solution. The subsequent polymerization after initiation of the chain reaction is expected to occur through the monomer-soaked fibers. This creates the observed high strength bonding between polymer fiber and gel, resulting in improved mechanical and elastic properties of the hydrogel.

13.

Although Malmonge is directed to providing an artificial articular cartilage material, it nowhere addresses the problem of providing adequate strength and tougher mechanical properties to the hydrogel; accordingly, it never suggests to include relatively large, swellable fibers in amounts of 10-70 wt% in the polymer gel.

Likewise, Kou nowhere addresses the problem of improving the toughness of polymer hydrogels, not to mention suggesting reinforcement with long, monomer soaked fibers for solving this problem.



As discussed above, Pissis describes a polymer gel network reinforced with a dispersion of nanometer-sized Nylon particles, which do not display any appreciable swelling in solution. Pissis is not at all concerned with further improving the toughness of the gels; hence, there are no pointers in Pissis for applying millimeter or greater sized swellable fibers for attaining this effect. At most, Pissis teaches the use of comminuted Nylon particles in concentrations not exceeding 10 wt%.

The invention teaches soaking up of the monomer solution into the fiber, as demonstrated in exhibit C, followed by polymerization of said monomers. As a result, polymers are formed straight through the long fiber molecules, providing a particularly robust bonding of the fiber to the polymer gel matrix. According to this procedure, improved anchoring of the reinforcing in material and toughness is obtained.


By contrast, since the hydrogel according to Pissis is prepared by polymerizing a watery suspension of Nylon nanoparticles and a mixture of monomer + crosslinker + initiator, a weight percentage of 10% at maximum of said nanoparticles in the gel can be attained before undesired agglomeration occurs (page 561, final sentence). Evidently, no soaking of monomer solution into these nanoparticles occurs. As such, Pissis clearly teaches away from the transverse polymerization of monomer-soaked fibers, in which agglomeration is not an issue and, accordingly, much more fiber (10-70% m/m) can be added.

While the Examiner plainly repeats that it would have been obvious to use the teachings of Malmonge combined with Pissis, Kou and Young, she does not provide any evidence of a teaching, suggestion or motivation therein, either explicit or implicit, for considering, let alone combining these particular references and arriving at the claimed invention. In the absence of any explanation in this respect, such mere combination of references constitutes inadmissible hindsight.

For these reasons, I respectfully submit that the invention as claimed in the instant application is non-obvious over Malmonge in view of Pissis and Young and over Malmonge in view of Pissis and Kou (and Young).

I declare further that all statements made herein of my own knowledge are true and that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application and any patent issuing thereon.

Printed Name J.M.R.J. HUYLE

Signed Name 

Date 15th of May 2009

Exhibit A

1. Huyghe J.M., Oomens C.W., Campen D.H. van, Heethaar R.M. Low Reynolds number steady flow through a branching network of rigid vessels: I. A mixture theory. *Biorheology* 26, 55-71 (1989).
2. Huyghe J.M., Oomens C.W., Campen D.H. van. Low Reynolds number steady state flow through a branching network of rigid vessels: II. A finite element mixture model. *Biorheology* 26, 73-84 (1989).
3. Huyghe J.M., Campen D.H. van, Arts T., Heethaar R.M. A two-phase finite element model of the diastolic left ventricle. *J. Biomechanics* 24, 527-538 (1991).
4. Huyghe J.M., Campen D.H. van, Arts T., Heethaar R.M. The constitutive behaviour of passive heart muscle tissue: a quasilinear viscoelastic formulation. *J. Biomechanics*, 24, 841-849 (1991).
5. Huyghe J.M., Arts T., Campen D.H. van, Reneman R.S. A porous medium finite element model of the beating left ventricle. *Am. J. Physiol.* 262, H1256-H1267 (1992)
6. Bovendeerd P.H.M., Arts T., Huyghe J.M., Campen D.H. van, Reneman R.S. Dependence of local ventricular wall mechanics on myocardial fiber orientation: a model study. *J. Biomechanics* 25: 1129-1140 (1992).
7. Campen D.H., Huyghe J.M., Bovendeerd P.H.M., Arts T. Biomechanics of the heart muscle. *Eur. J. Mech., A/Solids* 13: 19-41 (1994)
8. Bovendeerd P.H.M., Huyghe J.M., Arts T., Campen D.H., Reneman R.S. Influence of endocardial-epicardial crossover of muscle fibers on left ventricular wall mechanics. *J. Biomechanics* 27: 941-951 (1994)
9. Snijders H., Huyghe J.M. Janssen J.D. Triphasic finite element model of swelling porous media. *Int. J. Num. Meth. Fluids* 20: 1039-1046 (1995).
10. Oomens C.W.J., Heus H.J. de, Huyghe J.M., Nelissen L., Janssen J.D. Validation of triphasic theory for a mimic of intervertebral disk tissue. *Biomimetics* 3 : 171-185 (1995).
11. Huyghe J.M., Campen D.H. van, Finite deformation theory of hierarchically arranged porous solids: balance of mass and momentum. *Int. J. Engng. Sci.* 33, 1861-1871 (1995).
12. Huyghe J.M., Campen D.H. van, Finite deformation theory of hierarchically arranged porous solids: constitutive relations. *Int. J. Engng. Sci.* 33, 1873-1886 (1995).

13. Bovendeerd P.H.M., Huyghe J.M., Arts T., Campen D.H. van, Reneman R.S. Regional wall mechanics in the ischemic left ventricle : numerical modeling and dog experiments. *Am. J. Physiol.* 270 : H398-H410 (1996).
14. Bavel H. van, Wielders J., Drost M.R., Huyghe J.M., Huson A., Janssen J.D. Strain distribution measurements on the gastrocnemius medialis of the rat during passive stretch. *J. Biomechanics*, 29, 1067-1074 (1996).
15. Drost M.R., Snijders H., Willems P., Huyghe J.M., Janssen J.D. Confined compression of canine anulus fibrosus under chemical and mechanical load. *J. Biomech. Eng.*, 117, 390-396 (1996).
16. Huyghe J.M. Morphology and Mechanics of muscle : two or one ? *Eur. J. Morphol.* 34, 3-4 (1996).
17. Vankan W.J., Huyghe J.M., Janssen J.D., Huson A. A 3D finite element model of blood perfused rat gastrocnemius medialis muscle. *Eur. J. Morphol.*, 34, 25-30 (1996).
18. Vankan W.J., Huyghe J.M., Janssen J.D., Huson A., Poroelasticity of saturated solids with an application to blood perfusion. *Int. J. Engng. Sci.* 34 , 1019-1031 (1996).
19. Vankan W.J., Huyghe J.M., Janssen J.D., Huson A., Hacking W.J.G. and Schreiner W., Finite element analysis of blood flow through biological tissue . *Int. J. Engng. Sci.* 35 , 375-385 (1997).
20. Huyghe J.M., Janssen J.D. Quadriphasic mechanics of swelling incompressible porous media. *Int. J. Eng. Sci.* 35, 739-802 (1997).
21. Vankan W.J., Huyghe J.M., Drost M.R., Janssen J.D., Huson A. A finite element mixture model for hierarchical porous media. *Int. J. Num. Meth. Eng.* 40 , 193-210 (1997)
22. Houben G.B., Drost M.R., Huyghe J.M., Janssen J.D., Huson A. Non-homogenous permeability of canine anulus fibrosus. *Spine* 22 , 7-16 (1997).
23. Frijns A.J.H., Huyghe J.M., Janssen J.D. A validation of the quadriphasic mixture theory for intervertebral disc tissue. *Int. J. Engng. Sci.* 35, 1419-1429 (1997)
24. Vankan W.J., Huyghe J.M., Slaaf D.W., van Donkelaar C.C., Drost M.R., Janssen J.D., Huson A. Finite element simulation of blood perfusion in muscle tissue during compression and sustained contraction. *Am. J. Physiol.* 273, H1587-1594 (1997)
25. Vankan W.J., Huyghe J.M., van Donkelaar C.C., Drost M.R., Janssen J.D. Mechanical interaction between muscle contraction and blood flow. *J. Biomechanics* 31, 401-409 (1998).

26. Lanir Y., Seybold J., Schneiderman, Huyghe J.M. Partition and diffusion of sodium and chloride ions in soft charged foam: The effect of external salt concentration and mechanical deformation. *Tissue Engineering* 4, 365-378 (1998).
27. Huyghe J.M., Janssen J.D. Thermo-chemo-electro-mechanical formulation of saturated charged porous solids. *Transport in Porous Media* 34, 129-141, (1999).
28. Huyghe J.M. Intra-extrafibrillar mixture formulation of soft charged tissues. *J. Appl.Theor. Mech.* 37, 519-536 (1999)
28. Burger E.H., Smit T.H., Huyghe J.M. BMU-coupling is regulated by local patterns of fluid flow. *Bone* 28: S110 (2001)
29. van Donkelaar C.C., Huyghe J.M., Vankan J.W., Drost M.R. Spatial interaction between tissue pressure and skeletal muscle perfusion during contraction. *J. Biomechanics* 34: 631-637 (2001).
30. Eijkelkamp M.F., van Donkelaar C.C., Veldhuizen A.G., van Horn J.R., Huyghe J.M., Verkerke G.J. Demands for an artificial disc. *Int. J. Artif. Organs* 24, 311-321 (2001).
31. Huyghe J.M., Janssen C.F., C.C. Van Donkelaar, Lanir Y. Measuring principles of frictional coefficients in cartilaginous tissues and its substitutes. *Biorheology* 39: 47-53 (2002).
32. Huyghe J.M., Houben G.B., Frijns A.J.H., van Donkelaar C.C. An ionised/non-ionised dual porosity model of intervertebral disc tissue : experimental quantification of parameters. *Biomechanics and modelling in Mechanobiology* 2: 3-19 (2003).
33. Smit T.H., Huyghe J.M., Cowin S.C. A double porosity model of cortical bone: estimation of the linear isotropic parameters. *J. Biomechanics* 35: 829-835 (2002).
- 35.Kemenade P.M. van, Huyghe J.M., Douven L.F.A. Modelling of the skin water barrier. *Transport in Porous Media* 50: 93-109 (2003) .
36. Meerveld J. van, Molenaar M.M., Huyghe J.M., Baaijens F.P.T. Analytical solution of compression, free swelling and electrical loading of saturated charged porous media. *Transport in Porous Media* 50: 111-126 (2003).
37. Frijns A.J.H., Huyghe J.M., Kaasschieter E.F., Wijlaars M.W. Numerical simulation of deformations and electrical potentials in a cartilage substitute. *Biorheology* 40: 123-131 (2003).
38. van Loon R., Huyghe J.M., Wijlaars M.W., Baaijens F.T.P. 3D FE implementation of an incompressible quadriphasic mixture model. *Int. J. Num. Meth. Engng.* 57: 1243-1258 (2003)

39. Smit Th., Burger E., J.M. Huyghe, A case for strain induced fluid flow as regulators of BMU-coupling and osteonal alignment. *J. Min. Bone research* 17: 2021-2029 (2002)
40. Boerboom, R.A., Driessen N.J.B., Bouten C.V.C., Huyghe J.M., Baaijens F.T.P. Mechanically induced collagen fibre synthesis and degradation in the aortic valve. *Annals Biomed. Engineering* 31: 1040-1053 (2003).
41. Driessen N.J.B., Boerboom R.A., Huyghe J.M., Bouten C.V.C., Baaijens F.T.P. Computational analysis of mechanically induced collagen fibre remodelling in the aortic heart valve. *J. Biomech. Engng.* 125: 549-557 (2003).
42. Driessen N.J.B., Peters G.W.M., Huyghe J.M., Bouten C.V.C., Baaijens F.T.P. Modelling of continuously distributed fibres in soft connective tissues. *J. Biomechanics* 36:1151-1158 (2003).
42. Driessen N.J.B., Peters G.W.M., Huyghe J.M., Bouten C.V.C., Baaijens F.T.P. Erratum: Modelling of continuously distributed fibres in soft connective tissues. *J. Biomechanics* 36:1235 (2003).
43. Huyghe J.M., Cowin S.C. Preface on Physicochemical and electromechanical interactions in porous media. *Transport in Porous Media* 50: 1-3 (2003).
44. Van Donkelaar C.C., Daniels M.A., Huyghe J.M., Cell deformation in response to long-term hyperosmotic loading. *Acta Bioeng. Biomech.* 5: 1-10 (2003).
45. Huyghe J.M., van Loon R., F.T.P. Baaijens. Fluid-solid mixture theory and electromechanics: the simplicity of Lagrangian mixture theory. *Computational and Applied Mathematics* 23: 235-258 (2004)
46. Huyghe J.M., Smit Th. Comment les cellules de l'os ressentent-elles une tension mécanique ? *Archives of Physiology and Biochemistry* 112(suppl.): 48-50 (2004).
47. Kaasschieter E.F., Frijns A.J.H., Huyghe J.M. Mixed finite element modelling of cartilaginous tissues. *Math. Comput. Simulat.* 61 :549-560 (2003)
48. van Kemenade P.M., M.M.J. Houben, J.M. Huyghe, L.F.A. Douven. Do osmotic forces play a significant role in the uptake of water by human skin ? *Skin Res. Technol.* 10: 109-112 (2004)
49. Huyghe J.M. Uniaxial tensile testing of canine annulus fibrosus tissue under changing salt concentrations. *Biorheology* 41:255-261 (2004)

50. Huyghe J.M., Bovendeerd P.H.M. Advanced applications of mixture theory to biological media. *AMAS-lecture Notes 20*:227-278 (2004)
51. Huyghe J.M., Bovendeerd P.H.M. Introduction to biological mixture mechanics. *AMAS-lecture Notes 19*: 99-158 (2005)
52. Wilson W., van Donkelaar C.C., Huyghe J.M. A comparison between mechano-electrochemical and biphasic swelling theories for soft hydrated tissues. *J. Biomech. Engng.* 127: 158-165 (2005).
53. Huyghe J.M. Constitutive restriction on swelling. *Oberwolfach Reports 2*: 524 (2005)
54. Wilson W., Huyghe J.M., van Donkelaar C.C., A composition-based cartilage model for the assessment of compositional changes during cartilage damage and adaptation, *OA & Cart*, 14(6), 507-616, (2006)
55. Malakpoor M.K., Huyghe J.M., Kaasschieter E.F., An analytical solution of incompressible charged porous media. , *Z. Angew. Math. Mech.*, 9999(1), 1-15, (2006)
56. Schroeder Y., Wilson W., Huyghe J.M., Baaijens F.P.T., Osmoviscoelastic finite element model of the intervertebral disc, *European Spine Journal*, 15(Suppl), 361-371, (2006)
57. Wognum S., Huyghe J.M., Baaijens F.P.T., Influence of osmotic pressure changes on the opening of existing cracks in two intervertebral disc models, *Spine*, 31(16), 1783-1788, (2006)
58. Huyghe J.M., Wognum S., Baaijens F.P.T., Point of View - Response', *Spine*, 31(16), E527, (2006)
59. Wilson W., Huyghe J.M., van Donkelaar C.C, Depth-dependent compressive equilibrium properties of articular cartilage explained by its composition. *Biomech. Mod. Mechanobiol.* 6(1-2), 43-53, (2007).
60. Huyghe J.M., Molenaar M.M., Baaijens F.P.T., Poromechanics of compressible charged porous media using the theory of mixtures, *J. Biomech. Eng.* 129: 776-785 (2007).
61. Huyghe J.M., Analytical solution of a pressure transmission experiment on shale using electrochemomechanical theory, *ASCE J. of Engin. Mech.* 133(9), 994-1002, (2007).
62. Malakpoor M.K., Kaasschieter E.F., Huyghe J.M., Mathematical modeling and numerical solution of swelling of cartilaginous tissues. Part 1: Modeling of incompressible charged porous media, *ESAIM:M2AN* 41(4), 661-678, (2007).

63. Malakpoor M.K., Kaasschieter E.F., Huyghe J.M., Mathematical modeling and numerical solution of swelling of cartilaginous tissues. Part II: Mixed hybrid finite element solution., *ESAIM:M2AN*, 41(4), 679-712, (2007).
64. Y. Schroeder, S.J. Elliot, W. Wilson, F.P.T. Baaijens, J.M. Huyghe, Experimental and model determination of human intervertebral disc osmoviscoelasticity, *J. of Orthop. Res.*, 0, in press, (2007).
65. Y. Schroeder, S. Sivan, W. Wilson, J.M. Huyghe, A. Maroudas, F.P.T. Baaijens, Y. Merkher, Are disc pressure, stress and osmolarity affected by intra and extrafibrillar fluid exchange, *J. of Orthop. Res.*, 25(10), 1317-1324, (2007).
66. L.H. Cornelissen, C.W.J. Oomens, J.M. Huyghe, F.P.T. Baaijens, Mechanisms that play a role in the maintenance of the calcium gradient in the epidermis, *Skin Res Technol*, 13(4), 369-376, (2007).
67. J.M. Huyghe, W. Wilson, K. Malakpoor. On the thermodynamical admissibility of the triphasic theory of charged hydrated tissues. *J. Biomech. Engng.* (2009).

Exhibit B




Figure: The loading of a fiber-reinforced gel (left) and a non-fiber-reinforced gel (right) shown before loading (above) and after loading (bottom). The non-fiber-reinforced gel is subject to brittle fracture (right bottom). The fiber-reinforced gel remains mostly intact after loading (left bottom).

Exhibit C

Figure: The swelling of a fiber in a monomer solution of pHEMA as visualised under a light microscope. Time runs from top to bottom. The diameter of the fiber is seen to triple in this process. The volume change is correspondingly a factor 10 higher.

